

Amendments to the Specification

Please replace the first full paragraph under the heading Comparative Example C1 on page 34, starting with “Comparative Example C1,” with the following amended paragraph.

Comparative Example C1 was prepared according to the procedure described in WO 02/30484 Example 5015.

Please replace the table that starts on page 34 and ends on page 35 of the application as filed with the following amended table.

Example	Material	Initial Water Contact Angle (°) (hexadecane)	Post-abrasion Water Contact Angle (°) (hexadecane)	Post-base treatment Water Contact Angle (°) (hexadecane)
1	Z-Deal/APD/NCO-silane 1/2/4	100 (65)	85 (53)	92 (56)
2	Z-Deal/TETA/NCO-silane 1/2/6	105 (63)	83 (51)	90 (58)
3	HFPO-ester/AMPD/NCO-silane 1/1/2	112 (72)	80 (50)	95 (62)
4	HFPO-ester/DETA/NCO-silane 1/1/2	111 (68)	82 (52)	97 (56)
5	HFPO-ester/TETA/NCO-silane 1/1/3	106 (69)	80 (48)	92 (55)
6	HFPO-ester/TETA/NCO-silane 2/1/2	114 (72)	84 (53)	95 (60)
7	HFPO-SF diester/APD/NCO-silane	108(67)	86(55)	90 (55)
8	HFPO-SF diester/DETA/NCO-silane	105 (65)	84 (53)	90 (56)
9	HFPO-oligomeric ester/TETA/NCO-silane / chloropropylsilane	105 (63)	78 (48)	83(50)
10	Fomblin Z DEALTM /Aminoethanol/DESMOD URTM N-100/ APTES	110(65)	85(53)	----
11	Fomblin Z-DEALTM /	108(63)	90(50)	----

	Aminoethanol / DESMODURT TM N- 100/APTES/Octadecanol			
12	HFPO-oligomeric ester/Aminoethanol/N- 100/APTES	105(69)	82(52)	90(54)
13	HFPO-oligomeric ester/aminoethanol/N- 100/MPTMS	112 (71)	83 (55)	90 (54)
14	HFPO-oligomeric ester/TETA/NCO- silane/TEGME	103 (65)	85 (50)	88 (54)
15	Example 3/FC- 4430/IPA=3/1/12	107 (70)	83 (55)	85 (52)
C1	See WO 02/3848; Ex. 50 15	105 (64)	88(57)	61 (38)
C2	untreated	35 (<20)	25 (<20)----	22 (<20)----